

TECHNICAL DATA SHEET

TDS: CVV60136

MASONRY STABILISER

340/V601/36

DESCRIPTION:

Coo-Var Masonry Stabiliser is a binding and sealing solution for degraded and porous masonry.

RECOMMENDED USE:

Coo-Var Masonry Stabiliser is designed for use on unstable brick, screed or plaster prior to painting.

AVAILABILITY:

1 litre, 2.5 litre, 5 litre

FINISH:

N/A

COLOUR:

Clear

TYPICAL S.G. (SPECIFIC GRAVITY):

0.96 @ 20 °C

VOLUME SOLIDS:

28%

WET FILM THICKNESS W.F.T

110 microns

DRY FILM THICKNESS D.F.T

25 to 30 microns

EXPECTED SPREADING RATE:

9 sq.m / litre

@ 110 microns D.F.T

Coverage dependant on the porosity of the surface.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

20 sec. B4 cup @ 25 °C

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 2 hours @ 20 °C

Hard dry: 12 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours or overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

571 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or Roller

Thinner Thinners 14
(Max vol): (10%)

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning Thinners 14
solvent:

Recoat 12 hours or
interval: overnight

SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminants.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR
Email: info@coo-var.co.uk
www.coo-var.co.uk

MASONRY STABILISER**340/V601/36**

Remove all loose, flaking material.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

None - Apply direct to surface.

SUBSEQUENT COAT:

Suitable topcoat - check compatibility first.

REMARKS:**HEALTH AND SAFETY:**

See safety data sheet - SDS 10766

ISSUED:

23 May 2012

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: info@coo-var.co.uk

www.coo-var.co.uk